



Master Pure 2K Hardener

Hardener for 2K lacquers

Master Pure 2K Hardener is a highly efficient, isocyanate and aziridine free hardener that activates and strengthens the lacquer and is very easy to work with. The product has no CLP classifications.

- No CLP classifications
- Isocyanate and aziridine free
- 48 hours potlife
- Easy to mix

Application area

For lacquering new, untreated and newly-sanded wood floors in public areas with heavy traffic. Ideal for all types of wood. To be used together with WOCA lacquers.

Work description

Preparation

It is important that both wood and lacquer have a temperature of min. 15°C (preferably around 20°C) and air humidity of approx. 50%. Make sure that the room is well-ventilated for optimal evaporation and drying time. For the final sanding to bare wood, use grit 100-120 sandpaper or sanding pad. Vacuum thoroughly and wipe the floor down afterwards, using a tightly-wrung water-soaked mop/cloth. Please note: WOCA Intensive Wood Cleaner can help to remove contaminants from fully sanded wooden floors before priming or lacquering. Please allow floor to fully dry overnight. The floor must be completely dry before priming or lacquering. When priming, use WOCA Master Base Primer for newly sanded wood to reduce side bonding. Alternatively, try WOCA Master Multi Primer for exotic wood species or old wood previously treated with oil or wax.

Always Remember

Always remember to test on a less visible spot to check the compatibility of the surface with the product.

Please note

See technical Datasheet for waterbased lacquer for drying time and application.

Technical data

Density: 0.95-1.00 g/ml.

Shelf life: 3 years

Application Temperature: +15-25°C and approx. 50% air humidity.

Coverage: 8-10 m²/L

Colours: Colourless

Cleaning of tools: Use soap and water

Storage: +10-25°C. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer.

Packaging: 100 ML

Pot life: The mixture must be used within 48 hours. Shake/stir thoroughly before use.

Odour: Faint

Mixing ratio: 2% or 100 ml to 5 L lacquer.

Maintenance and related products

WOCA Denmark A/S
Tværvej 6
DK - 6640 Lunderskov
+45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.