



# Køkkenbordsolie

## Application area

## Work description

### Always Remember

Always remember to test on a less visible spot to check the compatibility of the surface with the product.

### Final sanding

Grit 120-150.

## Drying time

**Drying time:** 12-24 hours at 20°C

**Between coats:** 30-60 minutes at 20°C

**Light use:** 24 hours at 20°C

**Fully hard:** 7 days at 20°C

## Technical data

**VOC:** 295 g/l, maximum VOC content (A/i (SB)): 500 g/l.

**Density:** 0.90-0.95 g/ml.

**Shelf life:** 3 years

**Application Temperature:** +15-30°C and approx. 50% air humidity.

**Coverage:** 12-15 m<sup>2</sup>/L

**Cleaning of tools:** Use WOCA Solvent or turpentine

**Storage:** +10-25°C. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer.

**Viscosity:** 30-35 Sec. DIN Cup 4

**Odour:** Faint

**Solid content:** 70-75%

## Maintenance and related products

WOCA Denmark A/S  
Tværevej 6  
DK - 6640 Lunderskov  
+45 9958 5600  
info@wocadenmark.com  
wocadenmark.com

*This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all*

*previous versions.*