woodcare+



WOOD FLOOR LACQUER

This descritptin is only for test sunscribe

- Water-based clear lacquer.
- Provides a durable surface.
- Fast-drying and easy to apply.

Application area

For lacquering wooden surfaces and floors where a durable and easy-to-clean finish is desired. The lacquer must not be overcoated with solvent-based products.

Work description

Always Remember
Always remember to test on a less visible spot to check the compatibility of the surface with the product.

Final sanding
Grit 100-120.

Application day 1
Apply two even coats of undiluted lacquer along the length of the boards. Apply the lacquer wet-on-wet to avoid overlaps. Avoid pooling of lacquer and allow the surface to dry overnight.

Application day 2
Sand the surface lightly with 120–150 grit and vacuum thoroughly. Apply the final coat of lacquer no later than 24 hours after the first coats.

Please note
Water and colored liquids, such as red wine and coffee, should be wiped up immediately to prevent stains.

Drying time

Between coats : 2-3 hours at 20°C

Light use : 6-12 hours at 20°C

Recommendation : Can only be covered with carpets and washed after 7 days. Failure to observe the drying time may result in poor adhesion and durability.

Fully hard : 7 days at 20°C

Technical data

VOC: 0 g/l, maximum VOC content (A/e (WB)): 130 g/l.

Density: 1.00-1.10 g/ml.

pH-value: pH 7-8

Shelf life: 1 year

Application Temperature: +15-25°C and approx. 50% air humidity.

Coverage: 8-10 m²/L

Colours: Colourless - Silk-matt

Storage: +10-25°C. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer.

Packaging sizes: 5 L

Viscosity: 20-25 Sec. DIN Cup 4

Dilution: Undiluted

Odour: Faint

Mixing ratio: Ready to use. Do not dilute.

woodcare+

Maintenance and related products

WOCA Denmark A/S
Tværvej 6
DK - 6640 Lunderskov
+45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.