



UV Sanding Sealer

Excellent sanding properties and filling up smaller gaps

UV Sanding Sealer is very easy to sand and sanding paper will last long time. 100% UV and no VOC.

- Sanding paper will last long time
- Very transparent
- Smooth surface after sanding
- No VOC

Application area

All types of hardwood, softwood, solid wood and veneer.

Work description

Preparation

Surface need to be clean, dry and free from dust.

Intermediate sanding grits

Grit 240-320.

Please note

UV Sanding Sealer need full drying before next coat. It's mandatory to complete with full UV Lacquer system. UV Sanding Sealer can't stand alone

Number of coats

1

How to apply

UV Sanding Sealer should be applied with 1 coat with 10-40 gr/m². UV full cure 180 mJ/cm².

Cleaning of roller and pump use WOCA UV Cleaner № 800525

Drying time

Drying time : UV full cure 180 mJ/cm²

Technical data

VOC: 0 g/l, maximum VOC content (A/e (SB)): 400 g/l.

Density: 1.20-1.30 g/ml.

Shelf life: 2 years

Coverage: 15-40 g/m²

Colours: Natural

Packaging sizes: 20 L

Viscosity: 60-70 Sec. DIN Cup 6

Dilution: Undiluted

Specific gravity: 1.20-1.30 g/ml.

Solid content: 100% UV

Mixing ratio: Ready to use. Do not dilute.

Maintenance and related products

WOCA Denmark A/S
Tværvej 6
DK - 6640 Lunderskov
+45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.