

Matting paste for UV Oil



Create your own gloss level

Matting paste for UV-oils can be used adjusting the gloss level

- Customized gloss level
- Fit the customer's demand
- Easy mixing into WOCA UV-oils

Application area

Used in WOCA UV-oils

Work description

Preparation

The wood must be clean, dry and free from dust.

Please note

Add maximum 25% into WOCA UV-oils. The product must be stirred before use and mixed well into UV-oils with an electric mixer. Shelflife of UV-oil when added Matting paste is 6 months.

Drying time

Drying time : UV drying with Hg lamps, min. 600-800 mJ/cm² for each lamp.
Production speed 10 m/min. For pigmented systems, a combination of Gallium and Mercury lamps are preferred.

Technical data

Density: 1.20-1.30 g/ml.

Shelf life: 2 years

Specific gravity: 1.10-1.20 g/ml.

Maintenance and related products

Maintaining and cleaning

The industrial surface treatment can be maintained with WOCA maintenance products

WOCA Denmark A/S
Tværvej 6
DK - 6640 Lunderskov
+45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.