Hardfloor PU-2K Coating

For renovating LVT, vinyl and linoleum floors

WOCA Hardfloor PU-2K Coating is an effective maintenance solution that protects LVT, vinyl, and linoleum floors from daily wear and extends the floor's lifespan. The durable and easy-to-clean surface reduces dirt absorption and maintenance, making it ideal for high-traffic areas.

- Durable PU protection
- Extends the floor's lifespan
- Ideal for renovating existing floors
- Resistant to dirt and liquids
- Sustainable solution, renovation instead of new
- Reduced maintenance

Application area

Suitable for LVT, PVC, vinyl, and linoleum floors

Work description

Preparation
Identify the type of flooring (e.g., linoleum, PVC, LVT, laminate, or other relevant covering) and assess the condition of the surface. The substrate must be stable, dry, and suitable for renovation. Existing surface treatments, including wax, polish, maintenance film, or previous coatings, must be removed in accordance with the flooring manufacturer's instructions.

Always Remember
Always remember to test on a less visible spot to check the compatibility of the surface with the product.

Application day 1
The surface is cleaned of previous surface treatments according to the manufacturer's instructions, then the floor is sanded and cleaned.

Application day 2
When the floor is completely dry, apply WOCA Hardfloor PU Coating according to the instructions.

Please note
The substrate must be stable, dry, and suitable for renovation.

Number of coats
1-2

Drying time

Drying time : 24 hours at 20°C

Between coats : 2-3 hours at 20°C

Light use : 4-6 hours at 20°C

Surface Dry : 24 hours at 20°C

Recommendation : It is important that the surface is completely dry before applying WOCA Hardfloor PU Coating. Note: Linoleum has a longer drying time than other materials.

Fully hard : 5 days at 20°C

Technical data

VOC: 90 g/l, maximum VOC content (A/e (WB)): 130 g/l.

Density: 1.00-1.10 g/ml.

pH-value: pH 7-8

Shelf life: 2 years

Application Temperature: +15-25°C and approx. 50% air humidity.

Coverage: 8-10 m²/L

Colours: Colourless - Silk-matt

Cleaning of tools: Use water

Storage: +10-25°C. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer.

Packaging sizes: 4.5 L

Non-slip (DIN 51130): R9

Viscosity: 20-25 Sec. DIN Cup 4

Pot life: The mixture must be used within 4 hours. Shake/stir thoroughly before use.

Odour: Characteristic

Mixing ratio: 500 ml hardener to 4,5 L PU Coating

Maintenance and related products

Maintaining and cleaning
Regular cleaning and maintenance with WOCA Hardfloor Cleaner.

WOCA Denmark A/S
Tværvej 6
DK - 6640 Lunderskov
+45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.